

Pre-Dispersed Flatting Base

Color Solutions

Chroma-Chem[®] Synermix[®] FA-W-34

General Information

Synermix FA-W-34 is a dispersion of flatting agents in water. It provides simple stir-in incorporation, uniform and efficient gloss reduction and consistency.

Key Benefits

Synermix FA-W-34 is a dispersion of flatting agents in water. It provides simple stir-in incorporation, uniform and efficient gloss reduction and consistency.

Applications

- Aqueous Industrial coatings
- Aqueous Architectural coatings



Rev. 01/2023



Physical Properties

Property	Value
Appearance	Cloudy
Percent Solids	32 - 36%
Viscosity (Stormer)	70 – 90 KU
Grind N.S.	5.0 - 6.0 Hegman
Flash Point	225 °F (107 °C)
Weight per gallon	9.7 lbs.

Level of Usage

In most applications 5 % to 15 % of Synermix FA-W-34 will reduce 60° gloss by 40 to 60 units.

Synermix FA-W-34 is typically added at the let-down stage of the paint formulation with simple stirin. To ensure smooth, spec-free finishes, Synermix base should be diluted with 5% to 10% glycol while under moderate agitation.

The diluted product should then be slowly added to the coating under continued agitation. (Caution: excessive mixing at high shear may cause loss of efficiency).

Packaging

Synermix FA-W-34 is available in 46 Lbs pails and 500 Lbs drum containers.

Please contact your local Vibrantz Technologies representative for the packaging available in your region.

Shelf Life

Synermix FA-W-34 should be stored at temperatures between 40° F/5° C and 130° F/50° C.

When kept in an original unopened container, it will remain stable for four years from the date of manufacture

The information and recommendations contained herein are based on data we believe to be reliable and does not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. The data herein is determined using Vibrantz's standard test methods. Hazard and safety information with respect to this product is available in the applicable SDS. Vibrantz will not be liable under any circumstance for consequential or incidental damages, including but not limited to, lost profits resulting from the use of our products