

In-plant Colorants

Color Solutions

Colortrend® 877

Colortrend 877 color dispersions are high-strength, pourable color pastes recommended for inplant tinting of emulsion and water-based paints. All colorants have a 6 minimum fineness of grind (Hegman gauge) which makes Colortrend 877 dispersions are exceptionally suitable for the tinting of latex paints. They can also be used for the economical formulation of deep accent paints, thus avoiding the grinding of dry pigment.

Colortrend 877 dispersions contain a broad color spectrum, selected to satisfy all the tinting needs of the manufacturer and contractor.

General Information

Chemistry and Compatibility

Colortrend 877 dispersions are compatible with all types of latices such as:

- · Semi-Gloss and Gloss Latices
- · Polyvinyl Acetate
- · Alkyd Resin Emulsions
- · Acrylics
- · Water Type Coatings
- · Vinyl Acetate Ethylene Copolymers
- Alkyd Modified Latices
- Styrene Butadine



Other Uses

Colortrend 877 dispersions can be used in many types of emulsion products requiring coloring. For example: aqueous graining inks, wax emulsions for lumber marking, leather and floor polish, latex adhesives, coated papers, Christmas tree coloring, grass paints, emulsion fabric coatings, leather coatings, rubber latex compounds, aqueous plastics and foams, and artists' paints.



Permanence

The pigments used in Colortrend 877 colorants were selected to provide a wide range of hues, good durability, lightfastness, and alkali resistance. However, the lightfastness, alkali resistance, and weathering properties of pigments (particularly organic reds and yellows) depend a great deal on the coatings, substrate and application conditions. For positive verification of lightfastness and durability, we recommend that the colorants be tested under accelerated or actual weathering conditions in the coating system and on the substrates where they will be employed.

High Solar Exposure

When formulating with Colortrend 877 colorants, consideration must be given to special circumstances of use and their effect on colorant durability. Examples of such conditions are: tropical or subtropical climates, deserts and ocean-fronting locations. In each of these instances the solar radiation received is significantly greater than most environments. The use of organic pigments in these situations should be considered only after careful evaluation of the fastness of the colorant vehicle combination to ensure it will meet the expected performance. The most reliable method of testing is to expose the coating under the expected conditions of use.



| | Description | Typical Lbs/Gal | Specific Gravity | Composition by Weight | | | Composition by Volume | | | VOC | |
|--------------|-----------------------|--------------------|---------------------|------------------------|---------|----------------|------------------------|---------|-----------|---------|-----|
| Product Code | | | | Pig- ment Solids | Vehicle | Vola- tiles | Pig- ment Solids | Vehicle | Volatiles | Lbs/Gal | g/L |
| 877-2066 | Medium Azo Yellow | 9.6 | 1.16 | 34.6 | 6.7 | 58.7 | 25.2 | 7.8 | 67.1 | 1.9 | 224 |
| 877-2501 | Med. Perma-cal Yellow | 10.6 | 1.27 | 43.8 | 11.8 | 44.4 | 36.0 | 13.7 | 50.3 | 1.9 | 226 |
| 877-2505 | Hi Tint Azo Yellow | 9.5 | 1.13 | 28.0 | 8.9 | 63.1 | 20.4 | 10.0 | 69.7 | 1.9 | 225 |
| 877-2528 | Hansa Yellow | 11.3 | 1.37 | 48.3 | 10.9 | 40.8 | 28.2 | 25.8 | 46.0 | 2.3 | 270 |
| 877-2530 | L/F Light Yellow | 11.9 | 1.42 | 46.2 | 11.4 | 42.4 | 31.0 | 15.5 | 53.5 | 4.2 | 501 |
| 877-2553 | Hi-strength Yellow | 10.2 | 1.20 | 51.4 | 7.9 | 40.7 | 41.2 | 9.6 | 49.2 | 1.7 | 201 |
| 877-2554 | Hi-strength Yellow | 9.5 | 1.25 | 36.7 | 5.6 | 57.7 | 29.2 | 6.2 | 64.6 | 1.0 | 118 |
| 877-2823 | Hansa Yellow 10G | 11.3 | 1.37 | 49.7 | 7.2 | 43.1 | 34.6 | 9.4 | 55.9 | 2.2 | 261 |
| 877-4206 | Chromium Oxide | 17.0 | 2.04 | 64.0 | 7.1 | 28.9 | 25.6 | 14.8 | 59.6 | 2.7 | 329 |
| 877-5513 | Phthalo Green | 11.2 | 1.32 | 42.5 | 7.6 | 49.9 | 25.3 | 9.9 | 64.8 | 2.2 | 258 |
| 877-7027 | Phthalo Blue G/S | 9.6 | 1.13 | 24.4 | 10.2 | 65.5 | 16.9 | 11.2 | 72.0 | 1.6 | 194 |
| 877-7034 | Phthalo Blue I/S | 9.7 | 1.16 | 39.3 | 7.0 | 53.8 | 28.5 | 8.3 | 63.2 | 1.9 | 228 |
| 877-7227 | Phthalo Blue | 9.4 | 1.09 | 43.1 | 15.8 | 41.1 | 32.0 | 19.7 | 48.3 | 0.8 | 101 |
| 877-7505 | Ultramarine Blue | 13.1 | 1.56 | 60.0 | 8.6 | 31.4 | 39.0 | 13.2 | 47.8 | 2.0 | 241 |
| 877-8895 | Carbazole Violet | 11.0 | 1.30 | 33.0 | 18.4 | 48.6 | 16.8 | 24.1 | 59.1 | 4.4 | 531 |
| 877-9908 | Lamp Black | 10.9 | 1.30 | 46.0 | 9.3 | 44.8 | 32.4 | 11.7 | 55.9 | 2.3 | 270 |
| 877-9910 | Hi-Strength Black | 10.8 | 1.30 | 45.0 | 8.6 | 46.5 | 32.0 | 10.9 | 57.2 | 2.6 | 308 |
| 877-9918 | Tinting Black | 10.8 | 1.30 | 45.0 | 8.9 | 46.1 | 31.6 | 11.2 | 57.3 | 2.3 | 281 |
| 877-9921 | Econo Black | 10.6 | 1.27 | 44.1 | 4.0 | 52.0 | 30.5 | 4.9 | 64.6 | 2.2 | 269 |
| 877-9940 | Stain Black | 10.1 | 1.21 | 31.7 | 11.7 | 56.6 | 27.3 | 8.5 | 64.2 | 2.7 | 325 |
| 877-9998 | Carbon Black | 10.5 | 1.27 | 40.0 | 7.0 | 53.1 | 27.3 | 8.5 | 64.2 | 2.7 | 325 |

The information and recommendations contained herein are based on data we believe to be reliable and does not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. The data herein is determined using Vibrantz's standard test methods. Hazard and safety information with respect to this product is available in the applicable SDS. Vibrantz will not be liable under any circumstance for consequential or incidental damages, including but not limited to, lost profits resulting from the use of our products