

## High-strength colorants for decorative waterborne applications

Color Solutions

### Colortrend® 931

Colortrend 931 colorants are a high strength, economical range specially developed for POS and in-plant tinting of waterborne coatings.

#### Application

Vibrantz Technologies' Colortrend 931 technology consists of highly concentrated waterborne colorants for tinting of decorative waterborne coatings. Compatible with a variety of coatings, Colortrend 931 is a versatile range of colorants.

Due to their high color strength and batch-to-batch consistency, Colortrend 931 colorants can be used in both in-plant and POS settings. The system produces easily reproducible colors that are suitable for mixing in a variety of latex paints, enamels, woodstains and more.

#### Properties

With a broad selection of organic and inorganic colorants, the Colortrend 931 range offers a wide color space. The high pigment concentration of the colorants ensures cost effectiveness, without compromising on performance. The low-VOC system shows superior durability, light fastness, improved opacity and weather resistance. Colortrend 931 colorants typically contain 50 g/l of VOCs to prevent drying.



## Our Services

As a frontrunner in integrating tinting solutions, Vibrantz Technologies provides excellent service in the set-up of your tinting systems as well as smooth colorant technology conversions. Our technical support includes:

- Assurance of colorant and base paint compatibility
- System design, optimization and pigment selection
- Color matching and database development
- Equipment compatibility and sales support

Stringent production controls and processes ensure that all colorants are manufactured to rigid specifications for color shade, strength and rheology. The end result is assured color accuracy and reproducibility.

Name	Color	Pigment	Pigment content of colorant [%]	7-8Light Fastness of Pigment <sup>1</sup>		Weather Resistance of Pigment <sup>2</sup>		Density of Colorant (kg/m <sup>3</sup> )
				Mass	Tint	Mass	Tint	
9310030 KW <sup>3</sup>	White	PW 6	57	8	N.A.	5	N.A.	1951
9319930 BW	Black	PBk 7	46	8	8	5	5	1338
9319936 BO <sup>3</sup>	Black Oxide	PBk 11	57	8	8	5	5	1907
9311830 CW <sup>3</sup>	Yellow Oxide	PY 42	57	8	8	5	5	1889
9311831 CWF <sup>3</sup>	Yellow Oxide	PY 42	58	8	8	5	5	1804
9311030 FW <sup>3</sup>	Red Oxide	PR 101	56	8	8	5	5	2039
9312030 LW <sup>3</sup>	Umber	PY 42 / PR 101 / PBk 7	16	8	8	5	5	1744
9312032 YG <sup>3</sup>	Biva Yellow	PY 184	50	8	8	4-5	4-5	1954
9312530 AW	Yellow	PY 97	44	7-8	7	4-5	3	1247
9310430 QW	Magenta	PR 122	21	7	7-8	4	4-5	1181
9310730 HW	Red	PR 168/ PR 254	24	8 / 8	8 / 8	5 / 4-5	4-5 / 5	1342
9310732 RW	Red	PR 112	41	8	6	4-5	3	1239
9317230 EW	Blue	PB 15:1/ PB 15:3	38	8 / 8	8 / 8	5 / 5	4-5 / 4-5	1355
9317530 BG <sup>3</sup>	Turquoise Green	PB 28	53	8	8	5	5	1685
9314230 GY <sup>3</sup>	Green Oxide	PG 17	68	8	8	5	5	2305
9315530 DW	Green	PG 7	50	8	8	5	4-5	1412
9318830 JW	Violet	PV 23	19	8	8	5	4	1314

The values given in the table are guidance figures only. The data is obtained from pigment suppliers, individual testing is recommended.

<sup>1</sup> Light fastness is measured on an eight step blue scale, where 1 = very poor light fastness, 8 = excellent light fastness.

<sup>2</sup> Weather resistance is measured on a five step gray scale, where 1 = very poor weather resistance, 5 = excellent weather resistance.

The information and recommendations contained herein are based on data we believe to be reliable and does not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. The data herein is determined using Vibrantz's standard test methods. Hazard and safety information with respect to this product is available in the applicable SDS. Vibrantz will not be liable under any circumstance for consequential or incidental damages, including but not limited to, lost profits resulting from the use of our products