

Highest colorant strength for universal architectural applications

Color Solutions

Monicolor® A

Vibrantz Technologies' Monicolor universal colorants offer a vast selection of colors for the architectural market. Technical specifications within the paint industry are increasingly compounded by ever-changing environmental requirements. Stricter regulations apply to all products in the colorant and paint industry. At the same time, the amount and variety of architectural products such as alkyds and latexes for interior and exterior use continue to grow.

General information

Applications

Vibrantz Technologies' complete range of universal Monicolor colorants for architectural applications are suitable for mixing with a variety of latex paints, long oil alkyds, enamels and wood stains.

Properties

The pigmentation of Monicolor colorants has been formulated to meet the performance demands of architectural paints. The range satisfies key performance requirements such as light fastness, accuracy in pastels, opacity and cost effectiveness. There are additional economical yellow and red options in the Monicolor portfolio to ensure a good price/performance ratio. Monicolor colorants ensure accuracy and reproducibility at the point-of-sale. Color and color strength are volumetrically controlled.

Monicolor A

Monicolor A colorants contain <400 g/l of VOCs. Propylene glycol is used as a co-solvent, adding to efficient functionality and performance of the dispensing equipment.

Mixed systems

Monicolor colorants are fully compatible with each other and can be used interchangeably to create a customized tinting system.

The color experts at Vibrantz Technologies are at hand to create unique tinting systems that meet your needs, taking into account:

- Technical performance
- Existing POS equipment
- Required color space
- Future needs and budget
- Our services

As a frontrunner in integrating tinting solutions, Vibrantz Technologies provides excellent service in the set-up of your tinting systems as well as smooth colorant technology conversions. Our technical support includes:

- Assurance of colorant and base paint compatibility
- System design, optimization and pigment selection
- Color matching and database development
- Equipment compatibility and sales support

Stringent production controls and processes ensure that all colorants are manufactured to rigid specifications for color shade, strength and rheology. The end result is assured color accuracy and reproducibility.



Name	Color	Pigment	Pigment content of colorant [%]	Light fastness of pigment ¹		Weather resistance of pigment ²		Specific Gravity (S.G)
				Mass	Tint	Mass	Tint	
XT	White	PW 6	65	8	N/A	5	N/A	2.1
ZT	Citron yellow	PY 138	12	8	8	4-5	4	1.4
KS	Yellow	PY 74	20	7-8	6-7	4-5	3	1.3
US	Orange yellow	PY 83	29	7-8	6-7	4	3	1.3
RT	Yellow oxide	PY 42	55	8	8	5	5	1.8
PT	Orange red	PR 168	10	8	8	5	4-5	1.4
RS	Red	PR 112	20	8	6	4-5	3	1.3
VT	Red oxide	PR 101	50	8	8	5	5	1.9
ST	Umber	PBk7/ PY42/PR101	35	8	8	5	5	1.7
MG	Magenta	PR 122	20	7	7-8	4	4-5	1.2
FT	Violet	PV 23	2	8	8	5	4	1.4
MT	Blue	PB 15:4	7	8	8	5	4-5	1.4
MS	Blue strong	PB 15:3	28	8	8	5	4-5	1.3
LT	Green	PG 36	10	8	8	5	4-5	1.4
LS	Green strong	PG	20	8	8	5	4-5	1.4
TT	Black	PBk 7	9	8	8	5	5	1.5

The values given in the table are guidance figures only. The data is obtained from pigment suppliers, individual testing is recommended.

¹ Light fastness is measured on an eight step blue scale, where 1 = very poor light fastness, 8 = excellent light fastness.

² Weather resistance is measured on a five step gray scale, where 1 = very poor weather resistance, 5 = excellent weather resistance.

The information and recommendations contained herein are based on data we believe to be reliable and does not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. The data herein is determined using Vibrantz's standard test methods. Hazard and safety information with respect to this product is available in the applicable SDS. Vibrantz will not be liable under any circumstance for consequential or incidental damages, including but not limited to, lost profits resulting from the use of our products