




VIBRANTZ
TECHNOLOGIES™

Silicon carbide polishing slurry


Single-pass | SIC substrate

POLISHING PERFORMANCE


SI-FACE VS. C-FACE
AT 5.5 PSI



SI-FACE
MRR COMPARISON




REPEATABILITY TEST



The above data refers to Vibrantz's acidic SIC single-pass formulation.

DEFECT PERFORMANCE



RA = 0.619 A RQ = 0.760 A

The above data refers to Vibrantz's acidic SIC single-pass formulation.

ACIDIC SINGLE-PASS FORMULATION



- Appearance: Purple liquid
- Density: 1.02 g/ml
- Lbs/gal: 8.48
- pH: 4.25
- Percent solids: 3%

Product orders: surfacepolishing.americas@vibrantz.com
For more information visit vibrantz.com.



VIBRANTZ
TECHNOLOGIES™